

TRGOVSKA IMENA TEKSTILNIH VLAKEN

Dodatne informacije: izr. prof. dr. Urša Stankovič Elesini; tel: (01) 200 3229; elektronski naslov: ursa.stankovic@ntf.uni-lj.si

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
A			
Abestron	azbest	Amersil	silikonski premaz
Accepta	poliester	Amilan	poliamid
A.C.E. Polyester	poliester	Anavor	poliester
Acele	acetat	Angelette	poliester
Aceta	acetat	Angelrest	poliester
Acetat	acetat	Anid	poliamid
Acethochlorin	klorovlakno	Anil	poliamid
Acribel	acetat	Anilana	poliamid
Acrilan	akril	Anso	poliamid (6)
Acrolon	akril	Antron	poliamid (6,6)
Acrybel	akril	Anywear	akril
Acrylast	akril	Arenka	aramid
Aerelle	poliester	Ariloft	acetat
Aeress	modakril	Arnel	triacetat
Aerocor	steklena vlakna	Astralene-C	poliester
Akryl	akril	Astroloft	poliamid
Akulene	poliester	Astrolon	poliamid
Akulon	poliamid	Astrolure	poliamid
Akwadyne	poliamid	A-Tell	poliester
Akwatek	poliester	Avicolor	acetat
Albene	acetat	Avisco	acetat
Algil	modakril	Avisco Vinion	klorovlakno
Alistran	kovinska vlakna	Aviscose	acetat
Alkvalon	poliamid	Avlin	poliester
Allerban	poliester	Avora FR	poliester
AM Cotton	bombaž	Ayrlin	poliamid
Amcel	acetat		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
B			
Barricaut	poliester	Biofresh	akril
Basofil	melamin	Biokryl	akril
Beltec	poliester	Blue C	poliamid (6,6)
Beta	steklena vlakna	Bonnel	akril
Bifil	poliamid	Bounce – Back	akril

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
C			
Cadon	poliamid	Chromspan	acetat
Calcium alginat	alginat	Cleerspan	elastan
Camalon	poliamid (6)	Clevyl	klorovlakno
Cantrece	poliamid (6,6)	Climarelle	poliester
Capima	poliamid	CM Cotton	bombaž
Capilene	poliester	CN Cotton	bombaž
Caplana	poliamid	Colobrite	poliester
Caprolan	poliamid (6)	ColorGuard	poliester
Captiva	poliamid	Colorfine	poliester
Caracule	polimerni premaz	Comforel	poliester
Caraloft	akril	Comfort Fiber	poliester
Cardable Glass	steklena vlakna	ComFortrel	poliester
Carolan	acetat	Comforlast	poliamid
Celacloud	acetat	Conductrol	akril
Celacrimp	acetat	Conex	aramid
Celafibre	acetat	Coney	aramid
Celafil	acetat	Conomet	kovinska vlakna
Celaire	acetat	Contro	elastodien
Celaloft	acetat	Cool Max	poliester
Celanese	□olyest	Corebond	poliester
Celbond	poliester	Cordura	poliamid (6,6)
Celebrate	acetat	Corterra	□olyester
Celon	poliamid	Courlene	polietilen
Celstar	acetat	Courlene	acetat
CEO α	poliester	Courtelle	akril

Cerex	Poliamid (6,6)	Crepset	poliamid (6)
CFF Fibrillated Fiber	akril	Creslan	akril
Chemfit	poliamid	Creslit	akril
Chemline	poliamid	Cresloft	akril
Chemlux	poliamid	Crinex	poliamid
Chinlon	poliamid	Chrinovyl	klorovlakno
Chlorin	klorovlakno	Cuprama	bakro
Chromelex	kovinska vlakna	Curel	elastan

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
D			
Dacron	poliester	Dralon	akril
Danulon	poliamid	Drawinella	acetat
Daplen	polipropilen	DriSilque	poliamid
Daran	akril	Drylene	polietilen
Darleen	elastodien	Dry Step	poliamid (6)
Darlspan	elastan	DSDN	poliamid (6,6)
Dayan	poliamid	DSP	poliester
DC-100	elastan	DuPont XTI	poliamid (6,6)
DC-700	elastan	Durasoft	poliamid
Dederon	poliamid	Duraspun	akril
Deeglas	steklena vlakna	Dura-Stran	kovinska vlakna
Delfion	poliamid	Duracel	poliamid
Dicel	acetat	Duraglass	steklena vlakna
Dien	poliamid	Duraspan	elastan
Diolen	poliester	Duratrek	poliamid
Diorid	modakril	Durette	aramid
Dolan	akril	DyeNAMIX	poliamid (6,6)
Dorix	poliamid	Dyneema	polietilen
Dorlastan	elastan	Dynel	modakril
Dorlon	poliamid		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
E			
Eastman 50	acetat	Enkasheer	poliamid (6)
Eastman 75	acetat	Enkatron	poliamid (6)
Easy Dye Fibers	poliester	Enkalure	poliamid (6)
ECF	poliester	Enkaswing	elastan
Eclipse	poliamid	Envilon	klorovlakno
EcoSpun	poliester	ESP	poliester
Eftrelon	poliamid	Estera	acetat
Efylon	poliamid	Esterweld	poliester
E-Glass	steklena vlakna	Estochrome	poliester
Ektafil	poliester	Estra	acetat
Elana	poliester	Estron	acetat
Elite®	poliamid	Evlan	viskoza
Encron	poliester	Evolutia	akril
Enka	poliamid (6)	Exlan	akril
Enkalon	poliamid		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
F			
Fairtex	kovinska vlakna	Fibravil	klorovlakno
Famco	steklena vlakna	Fibrite	polipropilen
Feneshield	steklena vlakna	Fibro	viskoza
Fenilon	aramid	Fibroceta	acetat
Fi-lana	akril	Fidion FR	poliester
Fiber C	acetat	Fi-lana	akril
Fiber D	akril	Filatex	elastodien
FiberGlass	steklena vlakna	Fillwell	poliester
Fiber K	elastan	Filifine	poliester
Fiber T	modakril	Finesse	poliester
Fiber 32	elastan	Flura	modakril
Fiberbrite 2000	poliester	Forlion	poliamid
Fiberfill	poliester	Fortrel	poliester
Fiberfrax	steklena vlakna	Frlon	poliamid
FiberLoc	poliamid (6,6)	Furon	poliamid
FiberSet	poliamid		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
G			
Galaxy	liocel	Glillon	poliamid
Garan	steklena vlakna	Glospan	elastan
Garanized	steklena vlakna	Golden Glow	poliester
Garanmat	steklena vlakna	Golden Touch	poliester
Garon	steklena vlakna	Graflon	modakril
Geilon	poliamid	Grilene	poliester
Gevetex	steklena vlakna	Grilon	poliamid
Ginny	akril	Grip	poliester
Glanzstoff	poliamid	Guup	poliamid
Glass Floss	steklena vlakna		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
H			
Hanover	poliamid (6)	Hochfest polyester	poliester
HardCut	poliester	Hollofil	poliester
Hardline	poliamid	Holofiber	poliester
Heatherdine	poliamid	Hydrofil nylon	poliamid
Heatherloft	acetat	Hydrofix	poliester
Helion	poliamid	Hydroflex	poliurestanski premaz
Hemlon	poliamid	Hydrotec	poliester
Hisilon	poliamid	Hydroweave	fluorovlakno
HMA	aramid	Hystron	poliester
HM-50	aramid	Hyten	Poliamid (6,6)

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
I			
Ice berg	steklena vlakna	Innova	Polipropilen
Imbue	poliester	Isolfil	polipropilen

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
J			
Jentell	poliamid		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
K			
Kanecaron	modakril	Kodel	poliester
Kapron	poliamid	Kodofill	poliester
Kashimilian	akril	Kodosoff	poliester
Kermel	aramid	Konex	aramid
Kevlar	aramid	Kuralon	vinilal
Kirklon Superbulk	poliamid	Kynar	poliester

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
L			
Lacea	polilaktid	Leavil	klorovlakna
Lactron	polilaktid	Lenzig	fluorovlakno
Lacty	polilaktid	Lilion	poliamid
Lame	kovinska vlakna	Loftguard	poliester
Lanacryl	akril	Loft-Set	poliamid
Lanese	acetat	Loftura	acetat
Lanon	poliester	Lonzona	acetat
Lansil	acetat	Luftura	acetat
Laselon	poliester	Lupralen	polietilen
Lastex	elastodien	Lurex	kovinska vlakna
Lastex S	elastan	Lusterloft	poliamid
Laton	elastodien	Lutrasil	polipropilen
Lavscan	poliester	Lycra	elastan
Leacril	akril	Lyocell	liocel

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
M			
Makrolan	akril	Microselect	poliester
Malon	akril	MicroSpun	poliester
Malora	kovinska vlakna	MicroSupreme	akril
Marlom	elastan	MicroSupplex	poliamid (6,6)
Marglass	steklena vlakna	Microtherm	poliester
Marisoun	acetat	Micro Touch	poliamid
Matinesse	poliamid	Minalon	acetat
Matte Touch	poliester	Minifil	poliamid
Mawus-M	poliester	Miraflex	steklena vlakna
Mawus-R	poliester	Mirlon	poliamid
Meraklon	polipropilen	Misrylon	poliamid
Meryl	poliamid	Mobilon	elastan
Metlon	kovinska vlakna	Modal by Lenzing	modal
Meubalese	acetat	Modal Sun	modal
Mewlon	vinilal	Modanyl	poliamid
Micro-loft	poliester	Modiglass	steklena vlakna
Microdenier Sensura	poliester	Monosheer	poliamid
Microlux	poliester	Movil	klorovlakno
MicroMattique	poliester	MP Faser	klorovlakno
MicroModal	modal	Multishear	poliamid (6)
Micronesse	poliester	MX108	poliamid
Microsafe (= Microsafe AM)	acetat	Mylar	kovinska vlakna

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
N			
Nailon	poliamid	NM1400	poliamid
Nannex	poliester	NM1500	poliamid
Narene	poliester	Nomelle	akril
National	poliamid	Nomex	aramid
Natrelle BCF	poliamid (6,6)	Nonbur N80	akril
NatureWorks PLA	polilaktid	Nonbur N90	akril
Nature Tex	poliester	Nopalon	acetat
Nefa-perlon	poliamid	No Shock	poliamid
Nefalon	poliamid	Numa	elastan
Negastat	poliester	Nycel	poliamid
Nerane	acetat	Nylco	kovinska vlakna
Nextel	keramična vlakna	Nylenka	poliamid
Niplon	poliamid	Nylex	poliamid
Nirlon	poliamid	Nylfil	kovinska vlakna
Nitiray	poliamid	Nylfrance	poliamid
Nitlon	akril	Nyloft	poliamid
Nitrilon	akril	Nylon	poliamid
Nitron	akril	Nylsuisse	poliamid
NM1000	poliamid	Nymarilon	akril
NM1103	poliamid	Nymcrylon	akril
NM1200	poliamid	Nytelle	poliamid

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
O			
Oceane	acetat	Orel	poliester
Onanth	poliamid	Orlon	akril
Opaceta	acetat	Ortalion	poliamid
OPTA	poliamid		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
P			
P-23	poliester	Ply-mat	steklena vlakna
P84	poliamid	Plyloc	poliamid
PA Cotton	bombaž	Polan	poliamid
Pa-Qel	akril	Polana	poliamid
Pan	akril	Polarguard	poliester
Pannakril	akril	Polartec	poliester
PE3100	poliester	Poliafil	poliamid
Pentec	poliester	Polifen	fluorovlakno
Perfilon	poliamid	Polymide	poliamid
Perlargon	poliamid	Polycotton	mešanica bombaža in poliembra
Perlofil	poliamid	Polyextra	poliester

Perlon	poliamid	Polymers	poliamid
Perlon-U	elastan	Polynosic	modal
Permasoft	poliamid (6)	Poval	vinilal
Phase 7	poliamid (6)	Powersilk	poliamid
Phenylon	aramid	PPG	steklena vlakna
Phillips 66 nylon	poliamid	Prelana	akril
Phrilon	poliamid	Prenylon	poliamid
Phrix perlon	poliamid	Primaloft	poliester
Pil-Trol	akril	Proof Ace	keramični mikroporozni premaz
Pittsburgh	steklena vlakna	ProModal	modal
PL	poliamid	Propilon	polipropilen
PL Cotton	bombaž	Puff Stuff	poliester

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
Q			
Qiana	poliamid	Qualloform	poliester
QualiFlo	poliester	Quilticel	acetat
Quallofil	poliester	Quintess	poliester

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
R			
Random-set	poliamid	Rexe	elastan
Random-tone	poliamid	Rhobene	acetat
Raybrite MF	kovinska vlakna	Rhodiacea	poliamid
Raybrite MM	kovinska vlakna	Rhodialin	acetat
Redon	akril	Rhodianil	poliamid
Reemay	poliester	Rhovyl	klorovlakno
Relon	poliamid	Ribbon straw	acetat
Remember	akril	Rilsan	poliamid
Rene 41	kovinska vlakna	Rilson	poliamid
Resistat	poliamid	Roica	elastan
Retrieve	poliester	Rolan	akril
Revere	elastodien	Royalbrite	poliamid (6)
Reymet	kovinska vlakna	Roylon	poliamid
Reynolds	kovinska vlakna	Ruvea	poliamid

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
S			
S-3	poliamid	Softec	poliester
Samson	poliamid	So-Lara	akril
Sanderit	poliamid	SolarMax	poliamid (6,6)
Saniro	modakril	Soalon	triacetat
Sanivq	modakril	Softalon	poliamid
Saran	klorovlakno	Softglow	poliamid
Sarille	viskoza	Sooflex	poliamid
Sayelle	akril	Spandaven	elastan
Schwarza-polyamid-p.	poliamid	Spandelle	elastan
Scultured estron	acetat	Spandex	elastan
SeaGard	poliamid	Spanzelle	elastan
Securelle	poliester	Sparkling	poliamid
SEF	modakril	Speckelon	poliamid
SEF Plus	akril	Spectra	polietilen
Sensura	poliester	Sportouche	poliamid
Seraceta	acetat	Spunloc	poliester
Seratelle	acetat	Spunnaire	poliester
Serelle	poliester	Stabilenka	poliamid
Serene	poliester	Stainmaster	poliamid (6,6)
Setilmat	acetat	Starbrite	poliamid (6)
Setilose	acetat	Staticgard	poliamid
Setina	acetat	Stay Gard	poliamid (6)
S-Glass	steklena vlakna	Steripur	poliester
Shanton	poliester	Steelon	poliamid
Shareen	poliamid (6)	Stilon	poliamid
Sheiflex	elastan	Stratifil	steklena vlakna
Shimmereen	poliamid (6)	Stratimat	steklena vlakna
Shoeflex	poliamid	Stretch-aire	poliester
Silene	acetat	Stretch ever	elastan
Silenka	steklena vlakna	Strialine	poliester
Silione	steklena vlakna	Stryton	poliamid
Silky Touch	poliamid (6)	Stylon	poliamid

Sillook	poliester	Substraight	poliester
Silpalon	akril	Sudalon	poliamid
Sinsen	akril	Superba	poliester
Skapalon	poliamid	Super Microft	poliester
SLR	acetat	Superwhite	acetat
Sluna	poliester	Supplex	poliamid (6,6)
Sno-Brite	akril	Supron	poliamid
Softglo	poliamid	Synflex-N	poliamid
Softalon	poliamid (6)		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
T			
T-400	elastomultiester	Textura	poliester
Tacryl	akril	ThermaStat	poliester
Tactel	poliamid (6,6)	Thermax	poliester
Tactesse	poliamid (6,6)	Thermolite	poliester
Tairilin	poliester	Thermoloft	poliester
Tango	poliamid	Thermovyl	klorovlakno
TB-tex	steklena vlakna	The Smart yarns	akril
Teca	acetat	Timbrelle	poliamid
Technora	aramid	Toplene	polipropilen
Tecron	poliamid	Toray-tetoron	poliester
Tefaire	fluorovlakno	Toray	poliamid
Teflon	fluorovlakno	Toraylon	akril
Tefzel	fluorovlakna	TR-draht	poliester
Teijin	acetat	Toyoflon	fluorovlakno
Teklan	modakril	Trevira	poliester
Telsar	polipropilen	Trialbene	acetat
Tenasco	viskoza	Trianti	steklena vlakna
Tencel	liocel	Tricel	triacetat
Tergal	poliester	Tricella	triacetat
Teriber	poliester	Triesta	triacetat
Terilen	poliester	Trilan	acetat
Terital	poliester	Trilene	poliamid (6)
Terlenka	poliester	Trevira	poliester
Teron	poliester	Tru-Ballisitc	poliamid (6)
Terylen	poliester	Typar	polipropilen
Terylene	poliester	Tyvek	polietilen
Toraylon	akril	Twaron	aramid
Tetoron	poliester	Twincel	viskoza
Tetlon	poliester	Twisloc	poliamid
Tetoron	poliester	Tynex	poliamid
Tetrolene	poliester	Type C	acetat
Tetron	poliester	Type F	acetat
Teviron	klorovlakna	Type K	acetat
Texlon	elastan	Type L	acetat
Textilion	poliamid		

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
U			
Ultra-bright	poliamid	Unel	elastan
Ultramid	poliamid	Unfla III	poliester
Ultra Micro Touch	poliamid (6)	Unicomb	steklena vlakna
Ultramirage	poliamid	Unifab	steklena vlakna
UltraFlo	poliester	Uniformat	steklena vlakna
Ultrastrand	steklena vlakna	Uniglass	steklena vlakna
Ultra Touch	poliamid (6)	Unirove	steklena vlakna
Ultravat	kovinska vlakna	Unistrand	steklena vlakna
Ultron	poliamid (6,6)	Unitope	steklena vlakna
Ultura	poliester	Urylon	elastan

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
V			
Vairin	elastan	Vinylon	vinilal
Valzer	akril	Virion	viskoza
Vanilon	poliamid	Viscolan	viskoza
Vanylon	poliamid	Viscose	viskoza
Varel	modakril	Vitel	poliester
Variline	poliamid	Vitro-fibras	steklena vlakna
Vegon	polipropilen	Vitro-Flex	steklena vlakna

Velicren	modakril	Vitron	steklena vlakna
Varlen	klorovlakno	Vitro-Strand	steklena vlakna
Verel	modakril	Vituf	poliester
Verranne	steklena vlakna	Vivana	poliamid
Versarech	poliester	Vive la Crepe	poliamid
Velicren	modakril	Vivrelle	poliamid
Vestan	poliester	Vmicelon	klorovlakno
Vetrotessile	steklena vlakna	Vonnel	akril
Vetrotex	steklena vlakna	Vycron	poliester
Vetrotex RMP	steklena vlakna	Vydran	akril
Vincel	modal	Vylor	poliamid
Vinol	vinilal	Vyrene	elastan

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
W			
Wear-Dated	poliamid (6,6)	Wetrelon	poliamid
WeatherBloc	akril	Wink	kovinska vlakna
Wellene	poliester	Wintuk	akril
Wellon	Poliamid (6,6)	Wolcrylon	akril
Wellstrand	poliamid (6,6)	Worry Free	poliamid

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
X			
X-Static	poliamid (+ srebro, ki je vezano v strukturo vlakna)	XTRA-taff	poliester

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
Y			
Yukon Fleece	poliester	Yulon	poliamid

Trgovsko ime	Ime po pravilniku	Trgovsko ime	Ime po pravilniku
Z			
Zantrel	poliamid (6)	Zefron	poliester
Zefkrome	akril	Zeftsport	poliamid (6)
Zefran	akril	Zeftron	poliamid (6)
Zefran	poliamid		